

ENGINEERED HORIZONTAL BAMBOO FLOOR 10MM

BOAT DECK DESIGN (EHBF10 - PS)



from vietnam only...

DESCRIPTION	PRODUCT ADVANTAGE	PRODUCT FEATURES	REFERENCE	OPTION	DIMENSION L X W X T (MM)	QUANTITY / BOX	QUANTITY / CONTAINER (20')
<ul style="list-style-type: none"> Engineered Bamboo Flooring, Groove & Groove profile with assembling plastic strip (wit/wo boat deck effect) Standard colors : Natural, Carbonate and Dark brown." 	<ul style="list-style-type: none"> Boat deck look with black plastic strip Easy assembly without glue High plastic quality in Polypropylene or polypropene "Do it yourself floor", Easy & precise assembly, Quick installation. 	<ul style="list-style-type: none"> Structure: bamboo layer of 2.5 mm thick + HMR MDF + backing layer. Horizontally pressed bamboo Micro bevel on long sides Glue: E0/E1 Finishing: 6 layers UV coating, semi-matt Moisture content: 6-9% 	<p>EHBF10 - PS</p>	<ul style="list-style-type: none"> No micro bevel on long sides HDF Core One more layer of aluminium oxyde finishing 	1,190 x 130 x 10 mm	1.856 m2	1,879 m2



PAYMENT TERM

Irrevocable L/C at sight or T/T

MINIMUM ORDER

• One container 20'

TEST AND CERTIFICATES

EN13489, EN 14342 / CE Marking

ISO 9001 vs 2000 Certificated

ENGINEERED HORIZONTAL BAMBOO FLOOR 10MM

BOAT DECK DESIGN (EHBF10 - PS)



from vietnam only...

SPECIFICATIONS OF THE PRODUCT

DIMENSIONS

Thickness: 10mm (tolerance ± 0.2 mm)
 Width: 130mm (tolerance ± 0.2 mm)
 Length: 1,190mm (tolerance ± 0.2 mm)

COLOR SHADES

Natural / Carbonate / dark brown (stain)

STRUCTURE

Bamboo wear layer: 2.5mm
 Core: HMR MDF (High Moisture Resistant MDF)
 Density 750kg/m³.
 Backing layer: Wood veneer.

BAMBOO SPECIE

Luong, Dendrocalamus, Membranaceus
 (North Vietnam / Laos)

PACKAGING

Planks per box: 12 planks
 M2 per box: 1.856
 Boxes per pallet: 46 boxes
 Kg per box: 15.5 Kg
 Quantity / 20'ctner: 1,879m²
 Pallet dimensions: 1,200x800 mm
 Packed in normal carton box covered by 100% recyclable plastic shrink film.

MANUFACTURING

MANUFACTURING

Acc. to NF EN 13489 july 2003.
 MC%: 6-9%
 Glues used: E1.

PROFILE / ASSEMBLY

Groove / groove profile.
 Assembly with a black PE plastic strip.
 No glue needed on the tongue / groove.

FINISHING

UV VARNISH COATING

6 coats of acrylic varnish, UV dried.

The dried coating resulting from the reactions with UV does not contain any free reactants or volatile substances.

INSTALLATION

• Floating: According to DTU 51.11 Dec 97, "Floating floor laying of parquets and laminated floor coverings with wood facing"

• Glued down: According to DTU 51.2 Aug 95, "laminated parquets"

• Installation on a low temperature heated floor, According to:
 - DTU 65.7 May 1993: Electrical sub-floor heating
 - DTU 65.14 July 2006: Hot water sub-floor heating
 Maximum authorised thermal resistance: 0.150m².K/W.

Glued down installation method advised.

MAINTENANCE

• For UV varnish coated flooring: Vacuum cleaner - Dust mop with cleaner / polish , renovator if needed.

USE CLASSIFICATION

• Use classification NF EN685 according to standard XP B53-69 january 2003.

This norm defines the areas and level of use of the flooring considering the wear layer thickness (restoration degree) and the hardness of the wood / bamboo specie used (wear resistance).

Hardness classification of the wood / bamboo species

Hardness class	Species
A: Brinell hardness: 10 to 20 N/mm ² .	Scotspine, Fir, Spruce, Alder
B: Brinell hardness: 20 to 30 N/mm ² .	Birch, Cherry, Chestnut, Teak, Walnut
C: Brinell hardness: 30 to 40 N/mm ² .	Luong bamboo (BH = 44 N/mm ²), Oak, Maple, Ash, Beech, Iroko, Moabi, Movingui
D: Brinell hardness: ≥ 40 N/mm ² .	Ipe, Jatoba, Merbau, Wenge

Use classification NF EN685 according to standard XP B53-69 january 2003.

Wear layer thickness t (mm)	Hardness Class				1st number: area	2nd number: trafic
	A	B	C	D		
2.5mm \leq t < 3.2mm	21	21	23	31	2: domestic	2: general
3.2mm \leq t < 4.5mm	21	22	31	33		
4.5mm \leq t < 7mm	22	23	33	34	3: commercial	3: high
7mm \leq t	22	31	34	41	4: Industrial	4: very high

• UPEC use classification following DTU51.11, CSTB specifications 2999: U2S-P2-E1-C0

• Fire resistance classification:

- According to Euroclass NF EN 14342, august 2005: Cfl-S1
- According to DTU "Wood-fire rules" 88, appendix 4: M3.

CE MARKING

According to Standard NF EN 14342, august 2005.

CE	CE group:	Thermal resistance (m ² .K/W): 0.056
	Density (kg/m ³) > 500	Thermal conductivity (W/m.K): 0.18
	Thickness (mm): 10	PCP content (ppm) < 0.01
	Formaldehyde emissions: E1	Breaking strength: N/A
	Reaction to fire: Cfl-S1	Biological durability: N/A